



Product Description

High Barrier, Water Based, Environmentally Friendly, Nanocomposite Barrier Coating for Transparent Sustainable Packaging

Coating Formulation Properties

Property	Typical Value	Units
Oxygen Permeability	0.1 - 0.2 0.0002 - 0.0005	cc- μ /m ² -day-atm cc-mil/100 in ² -day-atm
Solid Content	6.5 - 7.5	%
pH	6 - 8	
Viscosity	50-60	cP (30 rpm, 39.6 sec ⁻¹)

- Lower cost option
- Excellent optical transparency with no color
- Excellent barrier up to 65% RH
- Large enhancements of moisture barrier when coated on flexible packaging films
- Meets compostibility standards on bio-derived films
- Compliant with US and European food contact standards
- Targets dry food applications such as salty snacks, nuts, coffee
- Can be applied at high speeds using standard gravure coating methods
- No halogen, VOC's, or hazardous materials

InMat Inc.

216 Route 206 Suite 7, Hillsborough, NJ 08844 USA
(908) 874-7788 phone (908) 874-7672 fax

www.inmat.com



Nanolok™ EXC 1007V

Product Data Sheet

Product Description

High Barrier, Water Based, Environmentally Friendly, Nanocomposite Barrier Coating for Transparent Sustainable Packaging

Coated Film Properties

Base Film			PET 48 gauge	
Property	Units	RH		
Coating Thickness	micron		1.0 ± 0.1	
OTR 23C	cc/m ² -day-atm (cc/100 in ² -day-atm)	0%	0.1	(0.006)
		50%	0.2	(0.01)
		65%	3.5	(0.2)
MVTR 38C	0.7 um coating gm/m ² -day (gm/100 in ² -day)	85%	25	(1.6)
Adhesion	gm/inch	23C	>300	

Comparison of Coated and Uncoated Film

Film	Nanolok EXC coating thickness (microns)	MVTR 38C, 85% RH (gm/m ² -day-atm)
PET 48 gauge	None	45
	0.7	25
BOPP 80 gauge	None	8
	0.9	5
PLA 80 gauge	None	275
	0.8	120